


# KeraBlack®



**Elegant black glass-ceramic** showing RED display.



Optional **deep black finish** :  
achieved by applying an opaque layer  
to the underside.

**Our most popular  
black glass-ceramic  
cooking panel with  
more than 80 million  
in use worldwide.**

## Standards

KeraBlack® meets the mechanical specifications defined by European and US standards EN 60335-1, EN 60335-2-6 and UL858.

This product is available with or without bottom surface texture (pebbles).



**eurokera**

**NOTE:** Technical specifications are available upon request.

[www.eurokera.com](http://www.eurokera.com)

GLASS-CERAMIC PROPERTIES	UNITS	VALUE
<b>Mechanical</b>		
Density	g/cm <sup>3</sup>	2.54
Young's Modulus E	GPa	92
Torsion Modulus G	GPa	36
Poisson's Ratio		0.26
Knoop Hardness		600
Minimum mechanical bending strength	MPa	150
Minimum static load resistance (600 x 500mm - Thickness 4mm)	kg	100
Impact resistance : Norwegian Hammer EN60335-1 Pot drop EN60335-2-6 Ball drop/Pan drop UL 858		Pass
<b>Thermal</b>		
CTE (20-700°C)	10 <sup>-7</sup> .K <sup>-1</sup>	0 ± 1
Specific Heat (20-100°C)	J/g.K	0.9
Resistance to thermal gradients - thermal shock	°C	ΔTmax = 700
<b>Optical</b>		
Visible light transmission TLD65	%	1.3
<b>Electrical</b>		
Electrical resistivity log n at 250°C	Ω.cm	6.8
Electrical resistivity log n at 350°C	Ω.cm	5.4
Dielectric constant (1MHz, 25°C)		7.9
Loss tangent factor (1MHz, 25°C)		0.02
<b>Chemical</b>		
Hydrolitic resistance DIN 12111		HGB1
Acid resistance DIN 12116		Class 3
Alkali resistance DIN 52322		A1
<b>Sustainability</b>		
Recyclable	Arsenic Free	Water-friendly enamels

All data are based on typical values and are not intended as specifications.