

Onyka® Prestige

ONYKA



A textured black matte cooktop that enhances kitchen aesthetics, offering high scratch resistance and easy maintenance.

Standards

The Onyka® Collection meets the mechanical specifications defined by European and US standards EN 60335-1, EN 60335-2-6 and UL858.

*The **scratch-resistance** performance of the **Onyka® Collection has been tested and verified by TÜV SÜD**, an independent German Company, using EuroKera's internal methods.

All comparisons are made with a standard glossy glass-ceramic cooking surface, such as EuroKera's KeraBlack®.



eurokera

NOTE: Technical specifications are available upon request.

www.eurokera.com



Elegance with a **textured** matte finish: **80% less reflection** than our standard glass-ceramic surface.



Superior durability*: up to **10 times fewer** visible scratches than our standard glass-ceramic surface.



Hassle-free solution: exceptional **resistance to fingerprints** and **stains**, compared to our standard glass-ceramic surface.

GLASS-CERAMIC PROPERTIES	UNITS	VALUE
Mechanical		
Density	g/cm ³	2.54
Young's Modulus E	GPa	92
Torsion Modulus G	GPa	36
Poisson's Ratio		0.26
Knoop Hardness		600
Minimum mechanical bending strength	MPa	150
Minimum static load resistance (600 x 500mm - Thickness 4mm)	kg	100
Impact resistance: Norwegian Hammer EN60335-1 Pot drop EN60335-2-6 Ball drop/Pan drop UL 858		Pass
Thermal		
CTE (20-700°C)	10 ⁻⁷ .K ⁻¹	0 ± 1
Specific Heat (20-100°C)	J/g.K	0.9
Resistance to thermal gradients - thermal shock	°C	ΔTmax = 700
Electrical		
Electrical resistivity log n at 250°C	Ω.cm	6.8
Electrical resistivity log n at 350°C	Ω.cm	5.4
Dielectric constant (1MHz, 25°C)		7.9
Loss tangent factor (1MHz, 25°C)		0.02
Chemical		
Hydrolitic resistance DIN 12111		HGB1
Acid resistance DIN 12116		Class 3
Alkali resistance DIN 52322		A1
Surface Aspect		
Roughness Ra	µm	5.5
Gloss (B60)	u.a.	6.5
Sustainability		
Recyclable	Arsenic-free process	Water-washable enamels*

*Washable with water during the finishing process.

All data are based on typical values and are not intended as specifications.

06.05.2026